

CG 350



Product Info

Made from chlorinated and sulfonated polyethylene, Hypalon™ synthetic elastomer rubber is designed for demanding industrial environments. It has a Shore A hardness of 70 durometer. This material operates effectively across a wide range of temperatures. Its excellent resistance to environmental exposure and chemicals makes it suitable for a variety of specialized applications.

Performance

- It has exceptional resistance that withstands harsh weather, ozone, UV rays, abrasion, and oxidation for reliable long-term use.
- It performs well against acids, alkalis, and is flame-resistant, making it ideal for industrial settings.
- Has wide temperature tolerance that maintains integrity and performance in both cold and high-heat environments from temperature of -20°C to 120°C.



Technical Data

CG 350	Specification
Hardness "Shore A" (±5)	70 Durometer
Tensile strength	1000psi (≥7 MPa)
Elongation	≥250%
Density	1.35±0.05
Temperature range	-20 to +210 °F (-28 to 99°C)
Thickness (in stock)	1/32", 1/16", 3/32", 1/8", 3/16", 1/4"

**Disclaimer:
The information provided is based on vendor data and is believed to be accurate. However, Custom Gaskets Ltd. makes no express or implied guarantees regarding their accuracy, completeness, or reliability. The user is solely responsible for determining the suitability of this product for its intended use and ensuring compliance with all applicable laws and regulations.*

While most of the potential hazards are identified on the Safety Data Sheet (SDS), certain risks may not yet be identified. Custom Gaskets Ltd. shall not be held liable for direct, indirect, incidental, or consequential damages arising from the use of this information or any Custom Gaskets Ltd. products. Users are responsible for obtaining and implementing any updates or clarifications based on new information.